

EEC NEOHS5
 Bonded NdFeB Magnet at 25°C

$B_r = 4.2 - 4.8$ kG
 $H_C = 3.9 - 4.5$ kOe
 $iH_C = 14 - 18$ kOe
 $(BH)_{max} = 4.5 - 5.5$ MGOe
 Density: 5.0-5.5 g/cm³
 Required Magnetizing Field: ≥ 30 kOe
 Maximum Operating Temperature: 130°C
 α^* of B_r (25-100°C): -0.07%/°C
 β^* of iH_C (25-100°C): -0.42%/°C
 * Temperature coefficient

