

EEC NEOL8
Bonded NdFeB Magnet at 25°C

$B_r = 6.0 - 6.5$ kG
 $H_C = 4.7 - 5.0$ kOe
 $iH_C = 8 - 10$ kOe
 $(BH)_{max} = 7.5 - 8.5$ MGOe
 Density: 5.5-5.8 g/cm³
 Required Magnetizing Field: ≥ 30 kOe
 Maximum Operating Temperature: 120°C
 α^* of B_r (25-100°C): -0.11%/°C
 β^* of iH_C (25-100°C): -0.4%/°C
 * Temperature Coefficient

