

EEC NEOLS10
Bonded NdFeB Magnet at 25°C

$B_r = 6.7 - 7.2$ kG
 $H_C = 5.4 - 5.8$ kOe
 $iH_C = 9 - 12$ kOe
 $(BH)_{max} = 9.5 - 10.5$ MGOe
 Density: 5.8-6.1 g/cm³
 Required Magnetizing Field: ≥ 30 kOe
 Maximum Operating Temperature: 130°C
 α^* of B_r (25-100°C): -0.08%/°C
 β^* of iH_C (25-100°C): -0.39%/°C
 * Temperature Coefficient

