

EEC NEOT9
 Bonded NdFeB Magnet at 25°C

$B_r = 6.1 - 6.6$ kG
 $H_C = 5.0 - 5.6$ kOe
 $iH_C = 11 - 14$ kOe
 $(BH)_{max} = 8.5 - 9.5$ MGOe
 Density: 5.8-6.1 g/cm³
 Required Magnetizing Field: ≥ 30 kOe
 Maximum Operating Temperature: 150°C
 α^* of B_r (25-100°C): -0.13%/°C
 β^* of iH_C (25-100°C): -0.37%/°C
 * Temperature coefficient

